## IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): An aqueous dispersion of water-soluble polymers of ethylenically unsaturated anionic monomers, obtainable by free radical polymerization of the monomers in an aqueous medium in the presence of at least one stabilizer, wherein the polymerization is carried out in the presence of at least one water-soluble polymer from the groups consisting of

(a) graft polymers of vinyl acetate and/or vinyl propionate on polyethylene glycols, polyethylene glycols blocked at one or both terminal groups with alkyl, carboxyl or amino groups and/or

copolymers of alkyl polyalkylene glycol methacrylates and methacrylic acid and at least one water-soluble polymer selected from

(b) hydrolyzed copolymers of vinyl alkyl ethers and maleic anhydride in the form of the free carboxyl groups and in the form of the salts at least partly neutralized with alkali metal hydroxides or ammonium bases, and/or of water-soluble starch from the group consisting of cationically modified potato starch, anionically modified potato starch, degraded potato starch and maltodextrin, as a stabilizer.

Claim 2 (Original): The aqueous dispersion according to claim 1, wherein polyalkylene glycols having molar masses Mn of from 100 to 100 000 and polyalkylene glycols blocked at one or both terminal groups with alkyl, carboxyl or amino groups and having molar masses Mn of from 100 to 100 000 are used as water-soluble polymers of group (a).

Claim 3 (Currently Amended): The aqueous dispersion according to either of claims 1 and 2 claim 1, wherein hydrolyzed copolymers of vinyl alkyl ethers and maleic anhydride in the form of the free carboxyl groups and in the form of the salts at least partly neutralized with alkali metal hydroxides or ammonium bases and/or maltodextrin are used as watersoluble polymers of group (b).

Claim 4 (Currently Amended): The aqueous dispersion according to any of claims 1 to 3 claim 1, wherein hydrolyzed copolymers of vinyl methyl ether and maleic anhydride in the form of the free carboxyl groups and in the form of the salts at least partly neutralized with sodium hydroxide solution, potassium hydroxide solution or ammonia are used as watersoluble polymers of group (b).

Claim 5 (Currently Amended): The aqueous dispersion according to any of claims 1 to 4 claim 1, wherein

(a) graft polymers of vinyl acetate on polyethylene glycols having a molecular weight M<sub>n</sub> of from 1000 to 100 000

and

(b) hydrolyzed copolymers of vinyl methyl ether and maleic anhydride in the form of the free carboxyl groups and in the form of the salts at least partly neutralized with sodium hydroxide solution, potassium hydroxide solution or ammonia are used as watersoluble polymers.

Claim 6 (Currently Amended): The aqueous dispersion according to any of claims 1 to 5 claim 1, wherein

Preliminary Amendment

Docket No.: 284134US0PCT

(a) copolymers of alkyl polyalkylene glycol methacrylates and methacrylic acid

and

(b) at least one hydrolyzed copolymer of vinyl methyl ether and maleic anhydride

in the form of the free carboxyl groups and in the form of the salts at least partly neutralized

with sodium hydroxide solution, potassium hydroxide solution or ammonia are used as water-

soluble polymers.

Claim 7 (Currently Amended): The aqueous dispersion according to any of claims 1

to 6 claim 1, wherein monoethylenically unsaturated C<sub>3</sub>- to C<sub>5</sub>-carboxylic acids, vinylsulfonic

acid, styrenesulfonic acid, acrylamidomethylpropanesulfonic acid, vinylphosphonic acid

and/or the alkali metal or ammonium salts thereof are used as anionic monomers.

Claim 8 (Currently Amended): The aqueous dispersion according to any of claims 1

to 7 claim 1, wherein the polymerization of the anionic monomers is carried out in the

presence of other ethylenically unsaturated monomers.

Claim 9 (Currently Amended): The aqueous dispersion according to claim 8, wherein

the polymerization of the anionic monomers is carried out in the presence of at least one

monomer from the group consisting of acrylamide, methacrylamide, acrylic esters of

monohydric alcohols of 1 to 4 carbon atoms, methacrylic esters of monohydric alcohols of 1

or 2 carbon atoms, vinyl acetate, vinyl propionate, dialkylaminoethyl (meth)acrylates,

dialkylaminopropyl (meth)acrylates, diallyldimethylammonium chloride, vinylimidazole, and

quaternized vinylimidazole.

4

Claim 10 (Currently Amended): The aqueous dispersion according to any of claims 1 to 7 claim 1, wherein, in the free radical polymerization, acrylic acid is used in the absence of other monomers.

Claim 11 (Currently Amended): The aqueous dispersion according to any of claims 1 to 9 claim 1, wherein the polymerization is additionally carried out in the presence of at least one crosslinking agent.

Claim 12 (Original): The aqueous dispersion according to claim 11, wherein triallylamine, pentaerythrityl triallyl ether, methylenebisacrylamide, N,N'divinylethyleneurea, dihydric alcohols of 2 to 4 carbon atoms which are completely esterified with acrylic acid or methacrylic acid, ethoxylated trimethylolpropane triacrylates, ethoxylated trimethylolpropane trimethacrylates, pentaerythrityl triacrylate, pentaerythrityl tetraacrylate and/or triallylmethylammonium chloride are used as the crosslinking agent.

Claim 13 (Currently Amended): A process for the preparation of aqueous dispersions of water-soluble polymers of ethylenically unsaturated anionic monomers by free radical polymerization of the monomers in an aqueous medium in the presence of at least one stabilizer, wherein the polymerization is carried out in the presence of at least one watersoluble polymer from the groups consisting of

graft polymers of vinyl acetate and/or vinyl propionate on polyethylene (a) glycols, polyethylene glycols blocked at one or both terminal groups with alkyl, carboxyl or amino groups, copolymers of alkyl polyalkylene glycol methacrylates and methacrylic acid, and at least one water-soluble polymer selected from

hydrolyzed copolymers of vinyl alkyl ethers and maleic anhydride in the form (b) of the free carboxyl groups and in the form of the salts at least partly neutralized with alkali metal hydroxides or ammonium bases, and/or maltodextrin, as a stabilizer at a pH of from 1 to 13.

Claim 14 (Currently Amended): The use of A method for thickening aqueous systems, the method comprising:

adding an aqueous dispersion according to any of claims 1 to 12 claim 1 as a thickener for to the aqueous systems.

Claim 15 (Currently Amended): The use The method according to claim 14, wherein the aqueous dispersion can be added to a thickening system in the total pH range.

Claim 16 (Currently Amended): The use The method according to claim 14 or 15, wherein the aqueous dispersion is used as an additive to paper coating slips, as thickeners for pigment print pastes and for water-based surface coatings, as thickeners for cosmetic formulations and for the surface treatment of leather.